

22R TYYPPIKÄYRÄT



Läpäisyarvot (%)

Lajite:	0 / 2	0 / 4	2 / 5	4 / 8	4 / 12	8 / 16
Seula (mm#):	G _{f85}	G _{f85}	G _{C 85/20}	G _{C 85/20}	G _{C 90/15}	G _{C 85/20}
0.063	5	4	1	1	1	1
0.125	11	8	2	2	2	2
0.25	22	16	2	2	3	3
0.5	38	27	3	2	4	3
1	60	42	4	3	4	3
2	95	65	7	3	5	3
4	100	92	68	5	5	5
5.6	100	98	98			
8	100	100	100	95	45	10
12.5	100	100	100	100	95	
16	100	100	100	100	100	95
32	100	100	100	100	100	100
64	100	100	100	100	100	100
H	726	650	486	412	368	324

Päiväys: 21.1.2015

Tuotannon sallitut poikkeamat täyttävät sekä by 43:n että standardin SFS-EN 12620 vaatimukset.

Lajite:	0 / 2	0 / 4	2 / 5	4 / 8	4 / 12	8 / 16
Seula (mm#):	G _{f85}	G _{f85}	G _{C 85/20}	G _{C 85/20}	G _{C 90/15}	G _{C 85/20}
0.063	± 3	± 3	± 1	± 1	± 1	± 1
0.125	± 3	± 3	± 2	± 2	± 2	± 2
0.25	± 4	± 4	± 2	± 2	± 3	± 3
0.5	± 5	± 5	± 3	± 2	± 4	± 3
1	± 8	± 6	± 4	± 3	± 4	± 3
2	± 5	± 8	± 7	± 3	± 3	± 3
4		± 5	± 8	± 5	± 5	± 5
5.6		± 2	± 2	± 5	-	-
8				± 5	± 10	± 10
12.5					± 5	-
16						± 5
32						
64						

