

33R TYYPIKÄYRÄT

Läpäisyarvot (%)

Lajite:	0 / 2	0 / 4	2 / 5	4 / 8	4 / 12	8 / 16
Seula (mm#):	G _{f85}	G _{f85}	G _{C 85/20}	G _{C 85/20}	G _{C 90/15}	G _{C 85/20}
0.063	7	5	2	1	1	1
0.125	16	10	2	2	2	2
0.25	29	19	2	2	2	2
0.5	48	29	2	2	2	2
1	70	45	2	2	2	2
2	95	65	15	2	2	2
4	100	88	72	5	5	2
5.6	100	98	98	9		
8	100	100	100	95	40	10
12.5	100	100	100	100	95	
16	100	100	100	100	100	95
32	100	100	100	100	100	100
64	100	100	100	100	100	100
H	758	656	495	410	355	317

Päiväys:

21.1.2015

Tuotannon sallitut poikkeamat täyttävät sekä by 43:n että standardin SFS-EN 12620 vaatimukset.

Lajite:	0 / 2	0 / 4	2 / 5	4 / 8	4 / 12	8 / 16
Seula (mm#):	G _{f85}	G _{f85}	G _{C 85/20}	G _{C 85/20}	G _{C 90/15}	G _{C 85/20}
0.063	± 3	± 3	± 1	± 1	± 1	± 1
0.125	± 3	± 3	± 2	± 2	± 2	± 2
0.25	± 4	± 4	± 2	± 2	± 2	± 2
0.5	± 5	± 5	± 2	± 2	± 2	± 2
1	± 8	± 6	± 2	± 2	± 2	± 2
2	± 5	± 8	± 5	± 2	± 2	± 2
4		± 5	± 7	± 5	± 5	± 2
5.6		± 5	± 5			
8				± 5	± 10	± 10
12.5					± 5	
16						± 5
32						
64						

