

35R TYYPPIKÄYRÄT



Läpäisyarvot (%)

Lajite:	0 / 2	0 / 4	2 / 5	4 / 8	4 / 12	8 / 16
Seula (mm#):	G _{f85}	G _{f85}	G _{C 85/20}	G _{C 85/20}	G _{C 90/15}	G _{C 85/20}
0.063	15	8	2	1	1	1
0.125	27	18	2	2	2	2
0.25	40	27	2	2	2	2
0.5	55	40	3	2	2	2
1	76	54	3	2	2	2
2	95	72	10	2	2	2
4	100	89	72	5	5	2
5.6	100	98	98	28	5	
8	100	100	100	95	40	10
12.5	100	100	100	100	95	
16	100	100	100	100	100	95
32	100	100	100	100	100	100
64	100	100	100	100	100	100
H	793	700	492	410	355	317

Päiväys: 21.1.2015

Tuotannon sallitut poikkeamat täyttävät sekä by 43:n että standardin SFS-EN 12620 vaatimukset.

Lajite:	0 / 2	0 / 4	2 / 5	4 / 8	4 / 12	8 / 16
Seula (mm#):	G _{f85}	G _{f85}	G _{C 85/20}	G _{C 85/20}	G _{C 90/15}	G _{C 85/20}
0.063	± 3	± 3	± 2	± 1	± 1	± 1
0.125	± 3	± 3	± 2	± 2	± 2	± 2
0.25	± 4	± 4	± 2	± 2	± 2	± 2
0.5	± 5	± 5	± 2	± 2	± 2	± 2
1	± 8	± 6	± 2	± 2	± 2	± 2
2	± 5	± 8	± 5	± 2	± 2	± 2
4		± 5	± 7	± 5	± 5	± 2
5.6		± 5	± 2			
8				± 5	± 10	± 10
12.5					± 5	
16						± 5
32						
64						

