

# 42R TYPPIKÄYRÄT

Läpäisyarvot (%)

Päiväys: 21.1.2015

Lajite:	0 / 2	0 / 4	2 / 5	4 / 12
Seula (mm#):	$G_{f85}$	$G_{f85}$	$G_{C 85/20}$	$G_{C 90/15}$
0.063	3	2	1	1
0.125	7	5	2	2
0.25	20	12	2	3
0.5	62	38	2	4
1	90	55	2	4
2	98	61	10	5
4	100	88	60	5
5.6	100	100	98	40
8	100	100	100	60
12.5	100	100	100	95
16	100	100	100	100
32	100	100	100	100
64	100	100	100	100
H	777	659	478	383

Tuotannon sallitut poikkeamat täyttävät sekä by 43:n että standardin SFS-EN 12620 vaatimukset.

Lajite:	0 / 2	0 / 4	2 / 5	4 / 12
Seula (mm#):	$G_{f85}$	$G_{f85}$	$G_{C 85/20}$	$G_{C 90/15}$
0.063	± 3	± 3	± 1	± 1
0.125	± 3	± 3	± 2	± 2
0.25	± 4	± 4	± 2	± 2
0.5	± 5	± 5	± 2	± 2
1	± 8	± 6	± 2	± 2
2	± 5	± 8	± 6	± 2
4		± 5	± 7	± 5
5.6		± 5	± 2	
8				± 10
12.5				± 5
16				
32				
64				

