

# LK300 TYPPIKÄYRÄT



Läpäisyarvot (%)

Päiväys: 21.1.2015

Lajite:	0 / 2	2 / 5	4 / 12
Seula (mm#):	$G_{f85}$	$G_{f85}$	$G_{C 90/15}$
0.063	1	1	1
0.125	5	2	2
0.25	12	2	2
0.5	35	2	2
1	60	2	4
2	88	10	4
4	100	86	7
5.6	100	98	12
8	100	100	40
12.5	100	100	95
16	100	100	100
32	100	100	100
64	100	100	100
H	700	504	361

Tuotannon sallitut poikkeamat täyttävät sekä by 43:n että standardin SFS-EN 12620 vaatimukset.

Lajite:	0 / 2	2 / 5	4 / 12
Seula (mm#):	$G_{f85}$	$G_{C 85/20}$	$G_{C 90/15}$
0.063	± 3	± 1	± 1
0.125	± 3	± 2	± 2
0.25	± 5	± 3	± 3
0.5	± 6	-	± 3
1	± 10	± 3	± 3
2	± 5	± 5	± 3
4		± 7	± 5
5.6		± 2	± 5
8			± 10
12.5			± 5
16			± 5
32			
64			



