

Betoni		Musta I	Musta II	Harmaa I	Harmaa II	Punainen I	Punainen II	Vihreä
Osa-aineet	Valkosementti	350 kg/m3	350 kg/m3	355 kg/m3	349 kg/m3	350 kg/m3	360 kg/m3	350 kg/m3
	33R 0/2			30 %	40 %			
	33R 2/5			20 %				
	33R 4/12			50 %	60 %			
	34R 0/2					30 %	30 %	
	34R 2/5					20 %	20 %	
	34R 4/12					50 %	50 %	
	35R 0/2	30 %	30 %					
	35R 2/5	20 %	20 %					
	35R 4/12	50 %	50 %					
	36R 0/2							30 %
	36R 2/5							20 %
	36R 4/12							50 %
	Elementti-Parmix	0,85 %	1,00 %	1,00 %	1,00 %	0,70 %	1,00 %	1,00 %
	Ilma-Parmix	0,07 %	0,11 %	0,08 %	0,08 %	0,06 %	0,08 %	0,08 %
	Ferroxon 618		3 %	0,30 %	0,30 %		0,30 %	0,50 %
	Ferroxon 410					3 %		
	Ferroxon 510					2 %		
	Ferroxon 750							3 %
V/S		0,47	0,45	0,46	0,5	0,50	0,42	0,5
Ilmamäärä heti		4,50 %	4,00 %	5,00 %	6,80 %	4,40 %	4,30 %	n. 4 %
Painuma heti		60 mm	40 mm	220 mm	60 mm	40 mm	55 mm	n. 40 mm
Puristuslujuus	1d	17,4 Mpa		27,5 Mpa	21,0 Mpa	18,0 Mpa		
	28d	62,6 Mpa		54,6 Mpa	46,0 Mpa	47,6 Mpa		
Kuvat								