

Environmental Data Sheet

Self-declaration based on Environdec Sub-PCR-H Cement and building limes (EN 16908)

Manufacturer:	Finnsementti Oy, Skräbbölenie 18, FI-21600, Parainen (FI)
Declared unit:	1 ton of cement
Production site(s):	Lappeenranta
Scope:	A1-A3
Methodology:	GCCA EPD Tool v2.0 / CML v4.7
Date of issue:	15.5.2020
Comment:	All information about goal and scope necessary for results interpretation by the EPD verifier are present in the latest version of the "LCA core model and database report".

Environmental impacts	SR		
	Lappeenranta	Kantvik	
Global warming potential, GWP (100 years)	757.99	791.72	kg CO2-eq.
Depletion potential of the stratospheric ozone layer, ODP	0.00	0.00	kg CFC 11-eq.
Acidification potential of soil and water, AP	1.18	1.72	kg SO2-eq.
Eutrophication potential, EP	0.39	0.77	kg PO43- -eq.
Formation potential of tropospheric ozone, POCP	0.09	0.10	kg ethylene -eq.
Abiotic depletion potential for non-fossil resources, ADP-elements	0.00	0.00	kg Sb-eq.
Abiotic depletion potential for fossil resources, ADP-fossil fuels	1597.22	2000.71	MJ
Human toxicity potential, HTP	214.92	229.98	kg p-DCB-eq.
Freshwater aquatic ecotoxicity potential, FAETP	51.26	92.30	kg p-DCB-eq.
Marine aquatic ecotoxicity potential, MAETP	112395.11	135298.26	kg p-DCB-eq.
Terrestrial ecotoxicity potential, TETP	4.35	19.48	kg p-DCB-eq.
Resource use			
Renewable primary energy used as energy resource	664.65	1289.60	MJ
Renewable primary energy used as raw materials	0.00	0.00	MJ
Total renewable primary energy	664.65	1289.60	MJ
Non-renewable primary energy used as energy resource	2146.95	2621.15	MJ
Non-renewable primary energy used as raw materials	0.00	0.00	MJ
Total non-renewable primary energy	2146.95	2621.15	MJ
Secondary material	157.40	157.40	kg
Renewable secondary fuels	515.40	515.40	MJ
Non-renewable secondary fuels	532.97	532.97	MJ
Net fresh water	6.85	10.31	m ³
Waste*			
Hazardous waste disposed	0.05	0.05	kg
Non-hazardous waste disposed	9.95	9.95	kg
Radioactive waste disposed	0.00	0.00	kg
Output flows*			
Components for re-use	0.00	0.00	kg
Materials for recycling	0.96	0.96	kg
Materials for energy recovery	0.42	0.42	kg
Exported energy	25.81	25.81	MJ
Extra indicators*			
Electricity use	111.71	111.71	kWh
Total dust	0.04	0.04	kg

* The contribution of activities situated upstream of the clinker manufacturing are not included in the results.