

# Environmental Data Sheet

Self-declaration based on Environdec Sub-PCR-H Cement and building limes (EN 16908)

Manufacturer:	Finnsementti Oy, Skräbbölenie 18, FI-21600, Parainen (FI)
Declared unit:	1 ton of cement
Production site(s):	Parainen
Scope:	A1-A3
Methodology:	GCCA EPD Tool v2.0 / CML v4.7
Date of issue:	15.5.2020
Comment:	All information about goal and scope necessary for results interpretation by the EPD verifier are present in the latest version of the "LCA core model and database report".

Environmental impacts	Parainen			
	Plus	Rapid	Pika	
Global warming potential, GWP (100 years)	611.70	740.42	763.76	kg CO2-eq.
Depletion potential of the stratospheric ozone layer, ODP	0.00	0.00	0.00	kg CFC 11-eq.
Acidification potential of soil and water, AP	1.00	1.17	1.22	kg SO2-eq.
Eutrophication potential, EP	0.29	0.34	0.36	kg PO43- -eq.
Formation potential of tropospheric ozone, POCP	0.06	0.07	0.07	kg ethylene -eq.
Abiotic depletion potential for non-fossil resources, ADP-elements	0.00	0.00	0.00	kg Sb-eq.
Abiotic depletion potential for fossil resources, ADP-fossil fuels	1107.02	1275.47	1338.89	MJ
Human toxicity potential, HTP	39.18	45.19	47.94	kg p-DCB-eq.
Freshwater aquatic ecotoxicity potential, FAETP	37.06	40.93	45.21	kg p-DCB-eq.
Marine aquatic ecotoxicity potential, MAETP	99933.02	114035.38	122053.43	kg p-DCB-eq.
Terrestrial ecotoxicity potential, TETP	1.72	2.04	2.15	kg p-DCB-eq.
<b>Resource use</b>				
Renewable primary energy used as energy resource	536.20	574.62	651.07	MJ
Renewable primary energy used as raw materials	0.00	0.00	0.00	MJ
Total renewable primary energy	536.20	574.62	651.07	MJ
Non-renewable primary energy used as energy resource	1635.07	1838.42	1982.38	MJ
Non-renewable primary energy used as raw materials	0.00	0.00	0.00	MJ
Total non-renewable primary energy	1635.07	1838.42	1982.38	MJ
Secondary material	226.87	63.81	67.63	kg
Renewable secondary fuels	271.74	331.52	341.00	MJ
Non-renewable secondary fuels	710.01	866.22	890.98	MJ
Net fresh water	5.65	6.14	6.69	m³
<b>Waste*</b>				
Hazardous waste disposed	0.05	0.06	0.06	kg
Non-hazardous waste disposed	7.99	9.74	10.02	kg
Radioactive waste disposed	0.00	0.00	0.00	kg
<b>Output flows*</b>				
Components for re-use	0.00	0.00	0.00	kg
Materials for recycling	0.49	0.60	0.62	kg
Materials for energy recovery	0.04	0.05	0.05	kg
Exported energy	36.25	44.23	45.49	MJ
<b>Extra indicators*</b>				
Electricity use	110.56	117.53	135.05	kWh
Total dust	0.04	0.05	0.05	kg

\* The contribution of activities situated upstream of the clinker manufacturing are not included in the results.