

A new White cement

# Valko

## SEMENTTI CEMENT

Rapid-hardening Portland  
Limestone cement  
CEM II/A-LL 52,5 R

**White cement** is ideal for the production of white and colored elements and concrete products. White cement is also ideal for the production of dry products, various mortars and fillers.

Cement properties	Requirements (SFS-EN 197-1)
Strength 2 d	≥ 30 MPa
Strength 28 d	≥ 52,5 MPa
Initial setting time	≥ 45 min
Soundness	≤ 10 mm
SO <sub>3</sub>	≤ 4,0%
Chloride content	≤ 0,10%

  

Cement composition	Requirements (SFS-EN 197-1)
Cement clinker	≥ 80%
Limestone	≥ 6% and ≤ 20%

  

Cement properties	Requirements (REACH N:o 1907/2006)
Cr6+	≤ 2 mg/kg

**FINNSEMENTTI**  
A CRH COMPANY

Finnsementti Oy  
FI-21600 Parainen, Tel. +358 201 206 200  
info@finnsementti.fi, name.surname@finnsementti.fi  
semnet.fi, finnsementti.fi

CE