

# Pika

## SEMENTTI CEMENT

Portlandcement  
CEM I 52,5 R

Thanks to its rapid strength development, **Pikacementti** is suitable for the production of elements and concrete that requires very fast demoulding. Special applications are prestressed concrete and high-strength concrete. By mixing Aggregate Cement is also well suited for the production of ready-mixed concrete.

Cement properties	Requirements (SFS-EN 197-1)
Strength 2 d	≥ 30 MPa
Strength 28 d	≥ 52,5 MPa
Initial setting time	≥ 45 min
Soundness	≤ 10 mm
Loss on ignition	≤ 5%
Insoluble residue	≤ 5%
SO <sub>3</sub>	≤ 3,0%
Chloride content	≤ 0,10%
Cr6+	≤ 2 mg/kg
Cement composition	Requirements (SFS-EN 197-1)
Cement clinker	≥ 95% and ≤ 100%

**FINNSEMENTTI**  
A CRH COMPANY

Finnsementti Oy  
FI-21600 Parainen, Tel. +358 201 206 200  
info@finnsementti.fi, name.surname@finnsementti.fi  
semnet.fi, finnsementti.fi

