

Rene

SEMENTTI

Portland composite-cement
CEM II/A-LL 52,5 R

Thanks to its rapid strength development, **Rene cement** is suitable for the production of elements and concrete that requires very fast demoulding. Special applications are prestressed concrete and high-strength concrete. By alloying the cement is also well suited for the production of ready-mixed concrete.

Cement properties

	Requirements (SFS-EN 197-1)
Strength 2 d	≥ 30 MPa
Strength 28 d	$\geq 52,5$ MPa
Initial setting time	≥ 45 min
Soundness	≤ 10 mm
SO ₃	$\leq 4,0\%$
Chloride content	$\leq 0,10\%$

Cement composition

	Requirements (SFS-EN 197-1)
Cement clinker	$\geq 80\%$ and $\leq 94\%$
Limestone	$\geq 6\%$ ja $\leq 20\%$

Cement properties

	Requirements (REACH N:o 1907/2006)
Cr6+	≤ 2 mg/kg

FINNSEMENTTI
A CRH COMPANY

Finnsementti Oy
FI-21600 Parainen, Tel. +358 201 206 200
info@finnsementti.fi, name.surname@finnsementti.fi
semnet.fi, finnsementti.fi

