Portland composite-cement CEM II/A-LL 52,5 R



Thanks to its rapid strength development, **Rene** is well-suited for precast production that requires a very fast demoulding.

Additionally, Rene cement can also accelerate ready-mix concrete production when added to conventional ready-mix concrete recipes.

Cement properties	Requirements (SFS-EN 197-1)
Strength 2 d	≥ 30 MPa
Strength 28 d	≥ 52,5 MPa
Initial setting time	≥ 45 min
Soundness	≤ 10 mm
SO <sub>3</sub>	≤ 4,0%
Chloride content	≤ 0,10%

Cement composition	Requirements (SFS-EN 197-1)
Cement clinker	≥ 80% and ≤ 94%
Limestone	≥ 6% ja ≤ 20%

Cement properties	Requirements (REACH N:o 1907/2006)
Cr6+	≤ 2 mg/kg



Finnsementti Oy FI-21600 Parainen, Tel. +358 201 206 200 info@finnsementti.fi, name.surname@finnsementti.fi semnet.fi, finnsementti.fi

