

Pika

SEMENTTI CEMENT

Portlandcement
CEM I 52.5 R

Thanks to its rapid strength development, **Pikacementti** is suitable for the production of elements and concrete that requires very fast demoulding. Special applications are prestressed concrete and high-strength concrete. Pikacementti is also well suited for ready-mixed concrete production when used in combination with other binders.

Cement properties	Requirements (SFS-EN 197-1)
Strength 2 d	≥ 30 MPa
Strength 28 d	≥ 52.5 MPa
Initial setting time	≥ 45 min
Soundness	≤ 10 mm
Loss on ignition	$\leq 5\%$
Insoluble residue	$\leq 5\%$
SO ₃	$\leq 3.0\%$
Chloride content	$\leq 0.10\%$

Cement composition	Requirements (SFS-EN 197-1)
Cement clinker	$\geq 95\%$ and $\leq 100\%$

Cement properties	Requirements (REACH N:o 1907/2006)
Cr6+	≤ 2 mg/kg

FINNSEMENTTI
A CRH COMPANY

Finnsementti Oy
FI-21600 Parainen, Tel. +358 201 206 200
info@finnsementti.fi, name.surname@finnsementti.fi
semnet.fi, finnsementti.fi

