

Rene

SEMENTTI

Portland composite-cement
CEM II/A-LL 52.5 R

Thanks to its rapid strength development, **Rene** is well-suited for precast production that requires a very fast demoulding.

Additionally, Rene cement can also accelerate ready-mix concrete production when added to conventional ready-mix concrete recipes.

Cement properties	Requirements (SFS-EN 197-1)
Strength 2 d	≥ 30 MPa
Strength 28 d	≥ 52.5 MPa
Initial setting time	≥ 45 min
Soundness	≤ 10 mm
SO ₃	≤ 4.0%
Chloride content	≤ 0.10%
Cement composition	Requirements (SFS-EN 197-1)
Cement clinker	≥ 80% and ≤ 94%
Limestone	≥ 6% ja ≤ 20%
Cement properties	Requirements (REACH N:o 1907/2006)
Cr6+	≤ 2 mg/kg

FINNSEMENTTI
A CRH COMPANY

Finnsementti Oy
FI-21600 Parainen, Tel. +358 201 206 200
info@finnsementti.fi, name.surname@finnsementti.fi
semnet.fi, finnsementti.fi

