

A new **lower carbon** White cement

**Rapid-hardening Portland
Limestone cement**
CEM II/A-LL 52,5 R

White cement is ideal for the production of white and colored elements and concrete products. White cement is also ideal for the production of dry products, various mortars and fillers.

Cement properties**Requirements (SFS-EN 197-1)**

Strength 2 d	≥ 30 MPa
Strength 28 d	≥ 52,5 MPa
Initial setting time	≥ 45 min
Soundness	≤ 10 mm
SO ₃	≤ 4,0%
Chloride content	≤ 0,10%

Cement composition**Requirements (SFS-EN 197-1)**

Cement clinker	≥ 80%
Limestone	≥ 6% and ≤ 20%

Cement properties**Requirements (REACH N:o 1907/2006)**

Cr6+	≤ 2 mg/kg
------	-----------

FINNSEMENTTI
A CRH COMPANY

Finnsementti Oy
FI-21600 Parainen, Tel. +358 201 206 200
info@finnsementti.fi, name.surname@finnsementti.fi
semnet.fi, finnsementti.fi

